Isotec International Inc



www.isotecintl.com • 800-234-6300

TECHNICAL DATA SHEET

IsoCoat HRN 5500

Isotec's IsoCoat HRN 5500 is a two-component hybrid low-pressure spray coating. This product was developed for contractors to use in various conditions and applications.

APPLICATIONS

- Boat Decks
- Cargo and Utility Vehicles
- Concrete Surfaces
- Containment
- Emergency Equipment linings
- Industrial Floors
- Truck Bed & Trailers Applications
- Various OEM Applications
- Waterproofing

PRODUCT ADVANTAGES

- 100% Solids
- Convenient 1:1 mixing ratio by volume
- Fast cure; can be handled/walked on in less than 1 hour

*1/-1:	:			-:£:
· values given	are not inten	ded to be t	isea iii sbei	cific preparation

Component Properties			
Color - ISO	Pale yellow		
Color - POL	Black		
Viscosity - ASTM D-2196 - 74°F, ISO	1340 cps		
Viscosity - ASTM D-2196 - 74°F, POL	540 cps		
Weight per gallon - ISO	9.44		
Weight per gallon - POL	8.77		
Reactivity Profile			
Ratio by Weight - ISO:POL	1.123:1.00		
Ratio by Volume - ISO:POL	1:1		
Gel Time - 100 gram sample, 74°F	14 - 16 Seconds		
Tack Free Time - 100 gram sample, 74°F	20 - 24 Seconds		
Sprayed Gel Time	5 Seconds		
Sprayed Tack Free Time	8 Seconds		
Full Cure	7 Days		
Typical Physical Properties			
Hardness - ASTM D2240 - Shore D	55 Shore D		
Tear Strength - ASTM D624, Die C	162 pli		
Tensile Modulus - ASTM D412	3200 psi		
Tensile Modulus - ASTM D412 - 100%	1120 psi		
Tensile Strength - ASTM D412	1300 psi		
Elongation - ASTM D412	120 %		

RECOMMENDED HANDLING INSTRUCTIONS

Isotec® International's Recommended Application and Handling Instructions

- -Use only in well-ventilated areas.
- -Wear chemically resistant rubber gloves, safety glasses, and an apron.
- -Avoid prolonged or repeated contact with skin.
- -In case of skin contact, wipe affected area with isopropyl alcohol, followed by soap and water.
- -In case of eye contact, flush eyes with water for 15 minutes and consult a physician.
- -If swallowed or comes into contact with eyes, seek medical attention immediately.
- -Always mix/roll POL side prior to use to ensure a homogenous product.

IsoCoat HRN 5500 was designed to be sprayed with lower pressure spray equipment. IsoCoat HRN 5500 can be sprayed at a temperature range of 75-95F. The recommended pressure settings are a material output of 45psi and the air regulator set to 60-70 psi.

STORAGE

Protect ISO and POL side from moisture. If the ISO side material is exposed to moisture, including moisture from the air, it will release CO2 gas. If placed in a sealed container, this gas can cause a dangerous buildup of pressure potentially resulting in injury or death. If the POL side is exposed to excess moisture and then applied it may cause weak or foamed material to be applied.

SAFETY

-Refer to the product SDS for all relevant safety information.

Date Modified 8/19/2019

Since Seller exercises no control over Buyers application or use of the product manufactured by Seller ("product") and since materials used with the product may vary, it is understood that:

- THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTIES OR MECHANTABILITY OR FOR ANY PARTICULAR PURPOSE. While all data presented in Seller's technical data sheet is based on the best information available to Seller and believed correct, such data is not to be construed as a warranty that the product will conform to such specifications. Such technical data sheets are subject to change without notice. Reported laboratory test results of fire redundancy in no way relates to the actual performance under fire conditions. Since all urethane systems are organic, they will burn.
- Reported laboratory test results of the color stability in no way relates to the actual performance upon exposure to light sources. Since all aromatic urethanes experience color degradation upon ultraviolet light exposure, Seller shall not be liable for any damages resulting from ultraviolet light color degradation of any aromatic urethane systems manufactured or sold by Seller.
- The liability of the Seller shall not exceed the purchase price and the Buyer shall not be entitled to nor the Seller be liable for any consequential, incidental, indirect or special damages resulting in any manner from the furnishing of the product.

www.isotecintl.com

"The Chemistry Behind Performance"®

(800) 234-6300